

Technical Data Sheet

Bayferrox[®] 917LO

Description

Type	Yellow pigment
Delivery form	Powder
Chemical class	Iron hydroxide - FeOOH
Color Index	Pigment yellow 42 (77492)
CAS-Nr.	20344-49-4

Colorimetric Data

Color values and tinting strength			
Reference	Bayferrox 917LO		11490019
Binder	Test paste based on a non drying alkyd resin		Test Method based on DIN 55 983 (1983)
	min.	max.	Test method
Full Shade			Based on DIN 6174
Delta-L*	-0,8	0,8	
Delta-E _{ab} *		1,4	
Reduction with titanium dioxide (1 : 5)			Based on DIN6174 & 55986
Color values after matching of the tinting strength parameter: Y, d. h.			
Delta-a*	-0,8	0,8	
Delta-b*	-0,8	0,8	
Delta-E _{ab} *		1,4	
Relative tinting strength [%]	95	105	Based on DIN 55 913

Technical Data Sheet

Bayferrox® 917LO

Specification

Technical Data	min.	max.	Test method
Sieve residue 325 Mesh [%]		0,05	Based on ASTM D-185
pH value	4,0	8,0	Based on ASTM D-1208

Informative technical data

	min.	max.	Test method
Fe ₂ O ₃ Content [%]	85	89	Based on ASTM D-50
Soluble Salts [%]		0,5	Based on ASTM D-1208
Oil absorption [g/100g]	22	28	Based on ASTM D-281
Particle shape		acicular	Electron micrographs
Tamped density [g/cm ³]	0,6	0,9	Based on ASTM D-787-11
Density [g/cm ³]	3,8	4,2	Based on ASTM D-153-75
Moisture content after production [%]		0,5	Based on ASTM D-280

Packaging

20 kg – paper bag

Transport and Storage

Protect against weathering.

Store in a dry place and avoid extreme temperature fluctuations.

Close bag after use to prevent moisture absorption and contamination.

Technical Data Sheet

Bayferrox® 917LO

Safety

Bayferrox 917LO is not classified as dangerous substance according to transport regulations (not classified).
The sample handling does not need special procedure.
The safety data sheet should be observed. It contains information on handling, product safety and ecology.

Use

Bayferrox 917LO is broadly used in several applications, however its use is not recommended in food and drugs.

Site address

LANXESS Indústria de Produtos Químicos e Plásticos Ltda
Rodovia Marechal Rondon km 139
18540-000 – Porto Feliz – São Paulo
Brazil
www.lanxess.com.br