

Technical Data Sheet

Preto 679

Description

Type	Black Pigment
Delivery form	Powder
Chemical class	Carbon black, Synthetic iron oxide – Fe ₃ O ₄
Color Index	Carbon black (77266), Pigment black 11 (77499)
CAS-Nr.	1333-86-4, 1317-91-9

Colorimetric Data

Color values and tinting strength			
Reference	Preto 679	15300197	
Binder	Test paste based on a non drying alkyd resin	Test Method based on DIN 55 983 (1983)	
	min.	max.	Test method
Reduction with titanium dioxide (1 : 5)			Based on DIN6174 & 55986
Color values after matching of the tinting strength parameter: Y, d. h.			
Delta-a*	-1,0	1,0	
Delta-b*	-1,3	1,3	
Delta-E _{ab} *		1,5	
Relative tinting strength [%]	95	105	Based on DIN 55 913

Technical Data Sheet

Preto 679

Specification

Technical Data	min.	max.	Test method
Sieve residue 325 Mesh [%]		0,5	Based on ASTM D-185
pH value	8,0	10,0	Based on ASTM D-1208

Informative technical data

	min.	max.	Test method
Soluble Salts [%]		0,5	Based on ASTM D-1208
Oil absorption [g/100g]	25	35	Based on ASTM D-281
Tamped density [g/cm ³]	0,5	0,8	Based on ASTM D-787-11
Density [g/cm ³]	2,4	2,8	Based on ASTM D-153-75
Moisture content after production [%]		2,0	Based on ASTM D-280

Packaging

25 kg – paper bag

Transport and Storage

Protect against weathering.

Store in a dry place and avoid extreme temperature fluctuations.

Close bag after use to prevent moisture absorption and contamination.

Technical Data Sheet

Preto 679

Safety

Preto 679 is not classified as dangerous substances according to transport regulations (not classified).

The sample handling does not need special procedure.

The safety data sheet should be observed. It contains information on handling, product safety and ecology.

Use

Preto 679 is broadly used in several applications, however its use is not recommended in food and drugs.

Site address

LANXESS Indústria de Produtos Químicos e Plásticos Ltda

Rodovia Marechal Rondon km 139

18540-000 – Porto Feliz – São Paulo

Brazil

www.lanxess.com.br

This information and our technical advice – whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.